
SORRO

REQUIREMENT OF A PRESERVATIVE TREATMENT

Against dry wood borer attacks:	Requires appropriate preservative treatment
In case of temporary humidification risk:	Requires appropriate preservative treatment
In case of permanent humidification risk:	Use not recommended

DRYING

Possible drying schedule

Drying rate:	Rapid to normal	Temperature (°C)			Air humidity (%)
		M.C. (%)	dry-bulb	wet-bulb	
Risk of distortion:	Slight risk	Green	50	47	84
Risk of casehardening:	No	40	50	45	75
Risk of checking:	Slight risk	30	55	47	67
Risk of collapse:	No	20	70	55	47
		15	75	58	44

This schedule is given for information only and is applicable to thickness < 38 mm.

It must be used in compliance with the code of practice.

For thickness from 38 to 75 mm , the air relative humidity should be increased by 5 % at each step.

For thickness over 75 mm , a 10 % increase should be considered.

SAWING AND MACHINING

Blunting effect:	Normal
Sawteeth recommended:	Ordinary or alloy steel
Cutting tools:	Ordinary
Peeling:	Good
Slicing:	No information available
Note:	Peeling is easy but not often used because logs are often ill-formed and with several knots.

ASSEMBLING

Nailing / Screwing:	Good
Gluing:	Correct

END-USES

Main known end-uses; they must to be implemented according to the code of practice.

Important remark: some end-uses are mentionned for information (traditional, regional or ancient end-uses).

Interior panelling
Flooring
Interior joinery
Current furniture or furniture components
Moulding
Blockboard
Wood frame house
Sculpture
Turned goods
Boxes and crates
